

US006936645B2

(12) United States Patent Hesler

(10) Patent No.: US 6,936,645 B2

(45) **Date of Patent:** Aug. 30, 2005

(54) METHOD OF FINISHING A DRYWALL AND A COMPOUND THEREFOR

- (75) Inventor: Travis Hesler, Biloxi, MS (US)
- (73) Assignee: DWC, LLC, Grand Bay, AL (US)
- (*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35

U.S.C. 154(b) by 178 days.

- (21) Appl. No.: 10/346,155
- (22) Filed: Jan. 16, 2003
- (65) Prior Publication Data

US 2003/0106468 A1 Jun. 12, 2003

Related U.S. Application Data

- (62) Division of application No. 09/941,041, filed on Aug. 28, 2001, now Pat. No. 6,569,497.
- (51) Int. Cl.⁷ C08L 3/00
- (52) **U.S. Cl.** **524/8**; 524/2; 524/582; 524/584; 428/401

(56) References Cited

U.S. PATENT DOCUMENTS

3,891,582 A 6/1975 Desmarais

4,039,492 A *	8/1977	Hamilton 524/26
4,404,314 A *	9/1983	Jabloner 524/519
5,079,042 A *	1/1992	Frings 427/403
5,277,712 A *	1/1994	McInnis 106/774
6,238,476 B1	5/2001	Sprinkle
6,295,794 B1	10/2001	Nordt et al.

^{*} cited by examiner

Primary Examiner—David W. Wu Assistant Examiner—Rip A Lee

(74) Attorney, Agent, or Firm—Keaty Professional Law Corporation

(57) ABSTRACT

The method for sealing a seam between adjacent structural panels significantly reduces the time for finishing a drywall in comparison with conventional methods, which use multiple applications of a joint compound to seal the seam. An drywall joint compound is mixed with a synthetic fiber, such as Colombian Fiber, or polypropylene, and sufficient water to facilitate soaking of the synthetic fiber and mixing with the joint compound. An optional liquid adhesive, such as liquid liquid adhesive for vinyl wallpaper, or water-based liquid adhesive, is added to the mixture. The mixture is then applied as one coat to the seam and allowed to dry. No subsequent coatings of the mixture are necessary.

5 Claims, 1 Drawing Sheet

MIXING A DRYWALL JOINT COMPOUND WITH WATER, SYNTHETIC FIBER AND LIQUID WALLPAPER ADHESIVE



APPLYING THE MIXTURE TO DRYWALL JOINTS



ALLOWING MIXTURE TO DRY